

Technical Data Sheet

Issue date: 18/04/2013 Date last modification: 11/05/2018

GRAPHICS - PROMOTIONAL

4-GL3B-08423 RI-FIX GLOSS WHITE AR864 ULTRA REMOVABLE WK135 N

Face Material

Gloss white monomeric vinyl.

Type Monomeric vinyl Colour and Finish Gloss white

Weight 210 g/m² \pm 10% ISO-536 Thickness 170 μ \pm 10% ISO 534-80

Adhesive

Solvent based ultra removable adhesive featuring very low adhesion and easy and clean removability from plastics and glass substrates.

Reference AR864 ultra removable Type Acrylic ultra removable

Min. Appl. Temp. +10°C Service Temp. -20°C/+100°C

Shear High

Tack Very low N/inch² Final Adhesion Very low N/inch

<u>Liner</u>

Type One side siliconised clay coated

Kraft

Colour and Finish White

Weight 135 g/m² PP-032 - ISO

±10% 536

Thickness 145 μ ±10% ISO 534
Transparency n.a. % DIN 53 147-64

Applications

Ideal for short to medium term window applications. Due to ultra removable repositioning adhesive, this product is suitable for application by any member of a retail team; however we recommend the product be applied to windows protected from external forces, for example: on the outside of a window but within a shopping mall.

Printing Methods

Excellent print results with HP latex, UV, solvent and ecosolvent ink-jet printing.

Ritrama recommends leaving a 5% border around your graphic when printing.

Ritrama recommends at least 24/48 hours of cure time before cutting

Testing for suitability between media, printers and inks is always recommended prior to use.

Shelf life

24 months, applicable only to the material delivered by Ritrama which has not undergone further processing, under the following *STORAGE CONDITIONS*:

- This material must be stored at a temperature of $22^{\circ}\text{C} \pm 2^{\circ}\text{C}$ and 50 \pm 5% of Relative Humidity.
- Storage area must be dry and clean.
- Keep the material in the original packaging when not used in order to protect it from dust and contamination.
- Do not expose to direct sunlight or heat sources.

All Ritrama products are subject to strict manufacturing controls to guarantee good quality products. The above information is based on research believed to be reliable, but does not constitute a warranty. All material should be tested by the purchaser to determine suitability of the product for their purposes.

All information is subject to change without prior notice.





