

GRAPHICS - Wide Format Ink Jet Print Media

Issue date : 05/01/2005
Date last modification : 30/04/2018**4-GL3B-02996 RI-JET 140 FLOOR TALKER GLOSS WHITE AP906 PERMANENT GREY WKPE144****Face Material**

Gloss white monomeric vinyl.

Type	Monomeric vinyl		
Colour and Finish	Gloss white		
Weight	134 g/m ² ±10%	ISO-536	
Thickness	100 µ ±10%	ISO 534-80	

Adhesive

Solvent based permanent acrylic adhesive featuring good water and cleaning agents resistance. High adhesion on a wide variety of substrates such as glass, ABS, PS, PVC. Unsuitable for apolar surfaces (like PE and PP). The grey pigmentation of the adhesive gives to the material excellent coverage performances. Ideal for floor graphics.

Reference	AP906 permanent		
Type	Acrylic permanent		
Min. Appl. Temp.	+10°C		
Service Temp.	-20°C/+140°C		
Shear	Very High		
Tack	High N/inch ²		
Final Adhesion	Very High N/inch		

Liner

Type	Siliconised two side PE Kraft		
Colour and Finish	White		
Weight	144 g/m ²	PP-032 - ISO	
	±10%	536	
Thickness	155 µ ±10%	ISO 534	
Transparency	n.a. %	DIN 53 147-64	

Applications

Advertising and promotional applications, designed to be applied to waxed commercial PVC and ceramic tile floor surfaces. To use in combination with the overlaminating film RI-121/200 FLOOR TALKER.

Printing Methods

The RI-JET series of ink-jet print media gives excellent print results with UV, solvent and eco-solvent ink-jet printing and with solvent based screenprinting. Testing for suitability between media, printers and inks is always recommended prior to use.

Shelf life

24 months, applicable only to the material delivered by Ritrama which has not undergone further processing, under the following **STORAGE CONDITIONS**:

- This material must be stored at a temperature of 22°C ± 2°C and 50 ± 5% of Relative Humidity.
- Storage area must be dry and clean.
- Keep the material in the original packaging when not used in order to protect it from dust and contamination.
- Do not expose to direct sunlight or heat sources.

All Ritrama products are subject to strict manufacturing controls to guarantee good quality products. The above information is based on research believed to be reliable, but does not constitute a warranty. All material should be tested by the purchaser to determine suitability of the product for their purposes. All information is subject to change without prior notice.

